

THIXATROL® PM 8056

Rheological Additive

Low temperature activation and highly effective organic thixotrope for solvent-borne and high solids Systems

GENERAL INFORMATION

THIXATROL PM 8056 is a 100 % active, seed resistant organic rheological additive. **THIXATROL PM 8056** provides high viscosity, thixotropy and thick layer sag control in high build systems that contain little solvent or are solvent-free.

CHEMICAL & PHYSICAL PROPERTIES

Composition	proprietary organic
Color / Form	fine off-white powder
Bulk density	0.25 g/cm ³ 2.08 lb/gal
Density	1.02 g/cm ³
Melting point	120 - 130 °C
Mean particle size	maximum 6 micron

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Industrial coatings
- Corrosion protective 2C epoxy primers
- Two component polyurethane top coat systems
- Two component solvent-free epoxy systems

KEY PROPERTIES

- Provides viscosity control, thixotropy and excellent very thick layer sag resistance.
- Is seed-resistant and allows low temperature activation, - processing, and packaging.
- Is a cost effective 100 % active powder that is highly active at already low loading levels
- Has a broad compatibility to various solvents.
- Shows no intercoat adhesion problems when overcoated with a topcoat.
- No negative influence on corrosion properties
- Excellent Mix(stress) stability of finished paint systems

INCORPORATION

The low temperature activation and broad solvent compatibility of **THIXATROL PM 8056** rheological additive makes sealant and paint manufacturing faster, easier and less expensive.

THIXATROL PM 8056 has specific processing temperature and dwell time requirements in order to develop optimum properties.

For complete activation, **THIXATROL PM 8056** should be introduced at the beginning of the manufacturing process in order to obtain sufficient wetting and dwell time. **THIXATROL PM 8056** will benefit from the temperature developed during the pigment dispersion phase to ensure maximum performance.

Recommended activation temperatures for high solids protective coatings (epoxy primers, polyurethane topcoats) are 40 - 70 °C (104 -158 °F)

Order of Addition

Typical high speed dissolver

1. Resin (and solvent if desired)
2. **THIXATROL PM 8056**
3. Pigments and extenders
4. Mix and disperse under 10 - 18 m/s tip speed until the desired minimum activation temperature is reached.
5. Continue with let down under moderate mixing conditions.

LEVELS OF USE

Typical levels of use for effective sag- and flow control range from 0.5 % to 2.0 % of the total system weight.

The optimum use level of **THIXATROL PM 8056** will vary depending on the chemistry of the system. When formulating a new system, a loading ladder study is recommended to determine the precise level of additive needed, the optimum activation temperature and the optimum stirring conditions.

continued...

THIXATROL[®] PM 8056

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

THIXATROL PM 8056 should be kept in a cool, dry location. Avoid stacking pallets in hot climates.

SHELF LIFE

THIXATROL PM 8056 has a minimum shelf life of 4 (four) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Aug. 2018

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563