

PB15:X PHTHALOCYANINE BLUE

MAIN CHARACTERISTICS

- Pigment Blue-crystal 15:X (C.I. 74160)
- Good overall fastness properties
- High tinting strength
- Wide range of coating applications

Heat fastness	>225°C*, 30 min
Light fastness	Excellent (8 on the blue wool scale)
Weather fastness	Excellent (5 on the grey scale)
Acid fastness	Excellent
Alkali fastness	Excellent
Solvent fastness	Excellent



RECOMMENDED PRODUCTS

Phthalocyanine Blue 1511C
 Reddish blue α-crystal modification (PB15:1)

Phthalocyanine Blue 1541C
 Greenish blue β-crystal modification (PB15:4)

Phthalocyanine Blue 1531C
 Greenish blue β-crystal modification (PB15:3)

* Paint