

PY151 BENZIMIDAZOLONE YELLOW

MAIN CHARACTERISTICS

- Pigment Yellow 151 (C.I. 13980)
- Clean greenish Yellow
- Good opacity
- Good rheological behavior
- Coloristic suitable to replace greenish Chrome Yellow grades
- Limited alkali resistance



Heat fastness	200°C*, 30 min
Light fastness	Good (7-8 on blue wool scale)
Weather fastness	Good (4-5 on grey scale)
Acid fastness	Excellent
Alkali fastness	Moderate
Solvent fastness	Good



RECOMMENDED PRODUCTS

Lysopac Yellow 5110C
Standard grade

Lysopac Yellow 5110P
Improved dispersibility

* Paint